

LABORATORY REPORT
HOWEL WOOD SANDSTONE

Petrographic Examination	fine grained Sandstone well sorted	
Water Absorption	kg/m ²	155
Compressive Strength	Mpa	31
Porosity		21.9%